

MSDS Report

Prepared For :	SHENZHENSHI JUZHAO DIGITAL CO., LTD. A2 Building, Republican Industrial Park, Republican Community, Shajing Street, Bao'an District, Shenzhen
Product Name:	Polymer Li-ion Battery
Model :	LP 432543
Nominal Voltage:	3.7V
Typical Capacity:	400mAh, 1.48Wh
Weight:	8.6g
Dimension :	45.0mm×26.0mm×4.5mm (L×W×T)
Prepared By :	Shenzhen TCT Testing Technology Co., Ltd. 1F, No.1 Building, No.1 Chongqing Road, Yibaolai Industrial Park, Qiaotou Village, Fuyong Town, Baoan District, Shenzhen
Report No.:	TCT150707M009

Written by: Cecily XiongApproved by: NInspected by: Carol XiongDate: 2015-07-28

Material Safety Data Sheet

Section 1- Chemical Product & Company Identification

Product Name: Polymer Li-ion Battery

Manufacture: SHENZHENSHI JUZHAO DIGITAL CO., LTD.

Address: A2 Building, Republican Industrial Park, Republican Community, Shajing Street, Bao'an District, Shenzhen

Contact Person: Miss Ding

Tel: +86-0755-61551688

Fax: +86-0755-61551648

Emergency Tel: +86-0755-61551688

E-mail: 2754839428@qq.com

Item Code: TCT150707M009

Section 2- Hazards Identification

Preparation hazards and classification	Not dangerous with normal use. Do not dismantle, open or shred Polymer Li-ion Battery the ingredients contained within or their ingredients products could be harmful.
Appearance, Color, Odor	Solid object with no odor, no color.
Primary Route(s) of Exposure	These chemicals are contained in a sealed stainless steel enclosure. Risk of exposure occurs only if the cell is mechanically, thermally or electrically abused to the point of compromising the enclosure. If this occurs, exposure to the electrolyte solution contained within can occur by Inhalation, Ingestion, Eye contact and Skin contact
Potential Health Effects:	ACUTE (short term): see Section 8 for exposure controls In the event that this battery has been ruptured, the electrolyte solution contained within the battery would be corrosive and can cause burns. Inhalation: Inhalation of materials from a sealed battery is not an expected route of exposure. Vapors or mists from a ruptured battery may cause respiratory irritation. Ingestion: Swallowing of materials from a sealed battery is not an expected route of exposure. Swallowing the contents of an open battery can cause serious chemical burns of mouth, esophagus, and gastrointestinal tract.

	Skin: Contact between the battery and skin will not cause any harm. Skin contact with contents of an open battery can cause severe irritation or burns to the skin. Eye: Contact between the battery and the eye will not cause any harm. Eye contact with contents of an open battery can cause severe irritation or burns to the eye. CHRONIC (long term): see Section 11 for additional toxicological data
Medical Conditions Aggravated by Exposure	Not applicable
Reported as carcinogen	Not applicable

Section 3- Composition/Information on Ingredients

Polymer Li-ion Battery is a mixture

Hazardous Ingredients (Chemical Name)	Concentration or concentration ranges (%)	CAS Number
Lithium Cobalt Oxide (CoLiO ₂)	15-40	12190-79-3
Graphite	10-30	1307-96-6
Phosphate(1-), hexafluoro-, lithium	10-30	21324-40-3
Copper	7-13	7440-50-8
Aluminum foil	5-10	7429-90-5
Nickel	1-5	7440-02-0

Labeling according to EC directives.

No symbol and risk phrase are required.

Note: CAS number is Chemical Abstract Service Registry Number.

N/A=Not apply.

Section 4- First Aid Measures

Inhalation	If contents of an opened battery are inhaled, remove source of contamination or move victim to fresh air. Obtain medical advice.
Skin contact	If skin contact with contents of an open battery occurs, as quickly as possible remove contaminated clothing, shoes and leather goods. Immediately flush with lukewarm, gently flowing water for at least 30 minutes. If irritation or pain persists, seek medical attention. Completely decontaminate clothing, shoes and leather goods before reuse or discard.
Eye contact	If eye contact with contents of an open battery occurs, immediately flush the contaminated eye(s) with lukewarm, gently flowing water for at least 30 minutes while holding the eyelids open. Neutral saline solution may be used as soon as it is available. If necessary, continue flushing during transport to emergency care facility. Take care not to rinse contaminated water into the unaffected eye or onto face. Quickly transport victim to an emergency care facility.
Ingestion	If ingestion of contents of an open battery occurs, never give anything by mouth if victim is rapidly losing consciousness, or is unconscious or convulsing. Have victim rinse mouth thoroughly with water. DO NOT INDUCE VOMITING. Have victim drink 60 to 240 mL (2-8 oz.) of water. If vomiting occurs naturally, have victim lean forward to reduce risk of aspiration. Have victim rinse mouth with water again. Quickly transport victim to an emergency care facility.

Section 5- Fire Fighting Measures

Flammable Properties	In the event that this battery has been ruptured, the electrolyte solution contain within the battery would be flammable. Like any sealed container, battery cells may rupture when exposed to excessive heat; this could result in the release of flammable or corrosive materials.
Suitable extinguishing Media	Use extinguishing media suitable for the materials that are burning.
Unsuitable extinguishing Media	Not available
Explosion Data	Sensitivity to Mechanical Impact: This may result in rupture in extreme cases Sensitivity to Static Discharge: Not Applicable
Specific Hazards arising from the chemical	Fires involving Polymer Li-ion Battery can be controlled with water. When water is used, however, hydrogen gas may evolve. In a confined space, hydrogen gas can form an explosive mixture. In this situation, smothering agents are recommended to extinguish the fire
Protective Equipment and precautions for firefighters	As for any fire, evacuate the area and fight the fire from a safe distance. Wear a pressure-demand, self-contained breathing apparatus and full protective gear. Fight fire from a protected location or a safe distance. Use NIOSH/MSHA approved full-face self-contained breathing apparatus (SCBA) with full protective gear.
NFPA	Health: 0 Flammability: 0 Instability: 0

Section 6- Accidental Release Measures

Personal Precautions, protective equipment, and emergency procedures	Restrict access to area until completion of clean-up. Do not touch the spilled material. Wear adequate personal protective equipment as indicated in Section 8.
Environmental Precautions	Prevent material from contaminating soil and from entering sewers or waterways.
Methods and materials for Containment	Stop the leak if safe to do so. Contain the spilled liquid with dry sand or earth. Clean up spills immediately.
Methods and materials for cleaning up	Absorb spilled material with an inert absorbent (dry sand or earth). Scoop contaminated absorbent into an acceptable waste container. Collect all contaminated absorbent and dispose of according to directions in Section 13. Scrub the area with detergent and water; collect all contaminated wash water for proper disposal.

Section 7- Handling and Storage

Handling	Don't handling Polymer Li-ion Battery with metalwork. Do not open, disassemble, crush or burn battery. Ensure good ventilation/ exhaust at the workplace. Prevent formation of dust. Information about protection against explosions and fires: Keep ignition sources away- Do not smoke.
Storage	If the Polymer Li-ion Battery is subject to storage for such a long term as more than 3 months, it is recommended to recharge the Polymer Li-ion Battery periodically. 3 months: -10℃~+40℃, 45 to 85%RH And recommended at 0℃~+35℃ for long period storage. The capacity recovery rate in the delivery state (50% capacity of fully charged) after storage is assumed to be 80% or more. The voltage for a long time storage shall be 3.7V~4.2V range. Do not storage Polymer Li-ion Battery haphazardly in a box or drawer where they may short-circuit each other or be short-circuited by other metal objects. Keep out of reach of children. Do not expose Polymer Li-ion Battery to heat or

fire. Avoid storage in direct sunlight.
Do not store together with oxidizing and acidic materials.

Section 8 - Exposure Controls/Personal Protection

Engineering Controls	Use local exhaust ventilation or other engineering controls to control sources of dust, mist, fumes and vapor. Keep away from heat and open flame. Store in a cool, dry place.
Personal Protective Equipment	Respiratory Protection: Not necessary under normal conditions. Skin and body Protection: Not necessary under normal conditions, Wear neoprene or nitrile rubber gloves if handling an open or leaking battery. Hand protection: Wear neoprene or natural rubber material gloves if handling an open or leaking battery. Eye Protection: Not necessary under normal conditions, Wear safety glasses if handling an open or leaking battery.
Other Protective Equipment	Have a safety shower and eye wash fountain readily available in the immediate work area.
Hygiene Measures	Do not eat, drink, or smoke in work area. Maintain good housekeeping.

Section 9- Physical and Chemical Properties

Physical State	Form: Solid
	Color: Silvery
	Odour: Monotony
Change in condition:	
pH, with indication of the concentration	Not applicable
Melting point/freezing point	Not available.
Boiling Point, initial boiling point and Boiling range:	Not available.
Flash Point	Not available.
Upper/lower flammability or explosive limits	Not available.
Vapor Pressure:	Not applicable

Vapor Density: (Air = 1)	Not applicable
Density/relative density	Not available.
Solubility in Water:	Insoluble
n-octanol/water partition coefficient	Not available.
Auto-ignition temperature	130°C
Decomposition temperature	Not available.
Odour threshold	Not available.
Evaporation rate	Not available.
Flammability (soil, gas)	Not available.
Viscosity	Not applicable

Section 10 – Stability and Reactivity

Stability	The product is stable under normal conditions.
Conditions to Avoid (e.g. static discharge, shock or vibration)	Do not subject Polymer Li-ion Battery to mechanical shock. Vibration encountered during transportation does not cause leakage, fire or explosion. Do not disassemble, crush, short or install with incorrect polarity. Avoid mechanical or electrical abuse.
Incompatible Materials	Not Available
Hazardous Decomposition Products	This material may release toxic fumes if burned or exposed to fire
Possibility of Hazardous Reaction	Not Available

Section 11 – Toxicological Information

Irritation	Risk of irritation occurs only if the cell is mechanically, thermally or electrically abused to the point of compromising the enclosure. If this occurs, irritation to the skin, eyes and respiratory tract may occur.
Sensitization	Not Available
Neurological Effects	Not Available
Teratogenicity	Not Available
Reproductive Toxicity	Not Available
Mutagenicity (Genetic Effects)	Not Available

Toxicologically Synergistic Materials

Not Available

Section 12-Ecological Information

General note:	Water hazard class 1(Self-assessment): slightly hazardous for water. Do not allow undiluted product or large quantities of it to reach ground water, water course or sewage system.
Anticipated behavior of a chemical product in environment/possible environmental impact/ ecotoxicity	Not Available
Mobility in soil	Not Available
Persistence and Degradability	Not Available
Bioaccumulation potential	Not Available
Other Adverse Effects	Not Available

Section 13 – Disposal Considerations

Product disposal recommendation: Observe local, state and federal laws and regulations.

Packaging disposal recommendation: Be aware discarded batteries may cause fire, tape the battery terminals to insulate them. Don't disassembly the battery. Completely discharge containers (no tear drops, no powder rest, scraped carefully). Containers may be recycled or re-used. Observe local, state and federal laws and regulations.

The potential effects on the environment and human health of the substances used in batteries and accumulators; the desirability of not disposing of waste batteries and accumulators as unsorted municipal waste and of participating in their separate collection so as to facilitate treatment and recycling;

Section 14 – Transport Information

This report applies to by sea, by air and by land;

The Polymer Li-ion Battery (model: LP 432543) tested according to the requirements of the UN manual of tests and Criteria, Part III, subsection 38.3;

The Polymer Li-ion Battery was protected so as to prevent short circuits. This includes protection against contact with conductive materials within the same packaging that could lead to short circuit;

The Polymer Li-ion Battery according to Section II/Section IB of PACKING INSTRUCTION 965, or Section II of PACKING INSTRUCTION 966~967 of the 2015 IATA Dangerous Goods regulations 56th Edition may be transported. and applicable U.S. DOT regulations for the safe transport of Lithium battery.

More information concerning shipping, testing, marking and packaging can be obtained from label master at <http://www.labelmaster.com/>.

The packaging shall be adequate to avoid mechanical damage during transport, handling and stacking.

The materials and pack design shall be chosen so as to prevent the development of unintentional electrical conduction, corrosion of the terminals and ingress of moisture.

The package must be handled with care and that a flammability hazard exists if the package is damaged;

Each package must be labeled with a Lithium battery handling label or in addition to the Class 9 hazard label.

With regard to transport, the following regulations are cited and considered:

- The International Civil Aviation Organization (ICAO) Technical Instructions.

- The International Air transport Association (IATA) Dangerous Goods Regulations.

UN number of lithium battery: UN3480 or UN3481;

UN Proper shipping name/Description (technical name): Lithium ion batteries or Lithium ion batteries contained in equipment or Lithium ion batteries packed with equipment;

UN Classification (Transport hazard class): Non dangerous;

Marine pollutant(Y/N): N;

- The International Maritime Dangerous Goods (IMDG) Code.

For Polymer Li-ion Battery by sea, provided that packaging is strong and prevent the products from short-circuit.

UN number of lithium battery: UN3480 or UN3481;

UN Proper shipping name/Description (technical name): Lithium ion batteries or Lithium ion batteries contained in equipment or Lithium ion batteries packed with equipment;

UN Classification (Transport hazard class): Non dangerous;

Marine pollutant(Y/N): N;

Special Provision: International maritime dangerous goods code (IMDG) 188, 230, 310, 348, 957;

- The US Hazardous Materials Regulation (HMR) pursuant to a final rule issued by RSPA

- The Office of Hazardous Materials Safety within the US Department of Transportations' (DOT)

Research and Special Programs Administration (RSPA)

Section 15 – Regulatory Information

OSHA hazard communication standard (29 CFR 1910.1200)

_____ Hazardous

_____ ☒ Non-hazardous

Section 16 – Additional Information

The information above is believed to be accurate and represents the best information currently available to us. However, Concorde makes no warranty of merchantability or any other warranty, express or implied, with respect to such information, and we assume no liability resulting from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes. Although reasonable precautions have been taken in the preparation of the data contained herein, it is offered solely for your information, consideration and investigation. This material safety data sheet provides guidelines for the safe handling and use of this product; it does not and cannot advise on all possible situations, therefore, your specific use of this product should be evaluated to determine if additional precautions are required.

The data/information contained herein has been reviewed and approved for general release on the basis that this document contains no export controlled information.

*****End of report*****

Report No.: TCT150707M009

Shenzhen TCT Testing Technology Co., Ltd.
1F, Building 1, Yibaolai Industrial Park, Qiaotou Village, Fuyong Town, Baoan District, Shenzhen,
Guangdong, P.R.C (518101)
Search Number: TCT150707M009C
Search System: <http://www.tct-lab.com/cn/search.asp>

Page 10 of 10

UN38.3 检测报告

UN38.3 Test Report

Client 委托方	Dong Guan Ding Chen New Energy Co., Ltd. 东莞市鼎辰新能源有限公司
Add. of Client 委托方地址	NO.2 Luo Qun pu street, Luo Ma Village, Qing Xi, Dong Guan, Guangdong, China. 东莞市清溪镇罗马村罗群埔二街
Samples Description 样品名称	Li-Polymer Battery 锂聚合物电池
Model/Type 型号规格	LP432543
Testing Laboratory 测试机构	Shenzhen NCT Testing Technology Co., Ltd. 深圳诺测检测技术有限公司 1 / F, No. B Building, Mianshang Younger Pioneer Park, Hangcheng Road, Gushu Xixiang Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区西乡街道固戍航城大道绵商青年创业园B栋第1层
Report No. 报告编号	NCT16010028B1-1
Issued Date 发行日期	Mar. 22, 2016
Test Conclusion 测试结论: Shown in the Conclusion of test report. 见检测报告结论页.	

Tested by 主检人:

Klaus Peng

Approved by 批准人:

Inspected by 审核人:

Hely Wang

Seal of NCT 报告单位 (盖章)

Date of Issue 签发日期: 2016. 03. 22



I、Sample Description 样品描述

Product Name 产品名称	Li-Polymer Battery 锂聚合物电池		Sample Model 样品型号	LP432543	
Manufacturer 制造商	DongGuan JinLu Battery Technology Co., Ltd. 东莞市劲鹿电池科技有限公司				
Address 地址	15#Rome Road QingXi Town, DongGuan City, GuanDong Province, China 广东省东莞市清溪镇罗马路 15 号				
Trade Mark 商标	N/A	Shape 形状	Prismatic 棱柱形	Size 尺寸 (L×W×T)	(45.0×26.0×4.5)mm
Nominal Voltage 标称电压	3.7V	Rated Capacity 额定容量	400mAh 1.48Wh	Limited Charge Voltage 充电限制电压	4.2V
Standard Charge Current 标准充电电流	80mA	Maximum Continuous Charge Current 最大持续充电电流	200mA	End Charge Current 结束充电电流	4mA
Cut-off Voltage 放电截止电压	3.0V	Standard Discharge Current 标准放电电流	80mA	Maximum Discharge Current 最大放电电流	400mA
Cell Number 组成电芯数量	1PCS		Cell Model 电芯型号	LP432543	
Receiving Date 接收日期	Mar. 02, 2016		Completing Date 完成日期	Mar. 22, 2016	

II、Standard 标准

Recommendations on the Transport of Dangerous Goods, Manual of Test and Criteria
(ST/SG/AC.10/11/Rev.5 Section 38.3/Amend.1 & ST/SG/AC.10/11/Rev.5 Section 38.3/Amend.2)
联合国《关于危险货物运输的建议书》第五修订版修正 1 和修正 2,第 38.3 节

III、Test Item 测试项目

- | | |
|---|--|
| T.1. ☒ Altitude simulation 高度模拟 | T.5. ☒ External short circuit 外部短路 |
| T.2. ☒ Thermal test 温度试验 | T.6. ☐ Impact / ☒ Crush 撞击/挤压 |
| T.3. ☒ Vibration 振动 | T.7. ☒ Overcharge 过充电 |
| T.4. ☒ Shock 冲击 | T.8. ☒ Forced discharge 强制放电 |

IV、Test Method and Requirement 测试方法和要求

Tests T.1 to T.5 shall be conducted in sequence on the same cell or battery. Tests T.6 and T.8 shall be conducted using not otherwise tested cells or batteries. Test T.7 may be conducted using undamaged batteries previously used in tests T.1 to T.5 for purposes of testing on cycled batteries.

用相同的电芯或电池按照顺序进行试验 T.1 至 T.5。试验 T.6 至 T.8 用没有进行其他试验的电芯或电池。为了测试循环后的电池，试验 T.7 可用试验 T.1 至 T.5 后没有损坏的电池。

Single cell batteries of B1#~B14# are full charged after one cycle;

Single cell batteries of B15#~B18# are full charged after fifty cycles;

Rechargeable cells of C19#~C23# are 50% charged after one cycle;

Rechargeable cells of C24#~C33# are full discharged after one cycle;

Rechargeable cells of C34#~C43# are full discharged after fifty cycle;

Test environment condition: ambient temperature: 15-25℃, ambient humidity: 40-70%

单电芯电池 B1#~B14#为一次循环满电状态;

单电芯电池 B15#~B18#为 50 次循环满电状态;

可充电电芯 C19#~C23#为一次循环后 50% 充电状态;

可充电电芯 C24#~C33#为一次循环完全放电状态;

可充电电芯 C34#~C43#为 50 次循环完全放电状态;

试验环境条件: 环境温度: 15-25℃, 环境湿度: 40-70%

In order to quantify the mass loss, the following procedure is provided:

$$\text{Mass loss (\%)} = (M1-M2)/M1 \times 100$$

质量损失的量化值, 可用以下公式计算:

$$\text{质量损失(\%)}=(M1-M2)/M1 \times 100$$

Where M1 is the mass before the test and M2 is the mass after the test. When mass loss does not exceed the values in Table below, it shall be considered as "no mass loss".

式中: M1 是试验前的质量, M2 是试验后的质量。如果质量损失不超过下表所列的数值, 应视为“无质量损失”。

Mass M of cell or battery 电芯或电池的质量	Mass loss limit 质量损失限值
M<1g	0.5%
1g≤M≤75g	0.2%
M>75g	0.1%

Leakage means the visible escape of electrolyte or other material from a cell or battery or the loss of material (except battery casing, handling devices or labels) from a cell or battery such that the loss of mass exceeds the values in Table above.

渗漏系指可以看到的电解液或者其他物质从电芯或者电池中漏出, 或电芯或电池中的物质损失 (不包括电池外壳、搬运装置、或标签), 失去的质量超过上表所列的数值。

In test T.1 to T.4, cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.

在测试 T.1 至 T.4 中, 电池须满足无渗漏、无泄气、无解体、无破裂和无起火, 并且每个试验电芯或电池在试验后的开路电压不小于其在进行这一试验前电压的 90%。

T.1. Altitude simulation 高度模拟**Test method 测试方法**

Batteries are stored at a pressure of 11.6 kPa or less for at least six hours at ambient temperature ($20 \pm 5^\circ\text{C}$).

试验电池被放置在压力等于或低于 11.6 kPa 和环境温度($20\pm5^\circ\text{C}$)下存放至少 6 小时。

Requirement 要求

Batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test battery after testing is not less than 90% of its voltage immediately prior to this procedure.

电池须无渗漏、无泄气、无解体、无破裂和无起火，并且每个试验电池在试验后的开路电压不小于其在进行这一试验前电压的 90%。

T.2. Thermal test 温度试验**Test method 测试方法**

Batteries are to be stored for at least six hours at a test temperature equal to $72 \pm 2^\circ\text{C}$, followed by storage for at least six hours at a test temperature equal to $-40 \pm 2^\circ\text{C}$. The maximum time interval between test temperature extremes is 30 minutes. This procedure is to be repeated 10 times, after which all test batteries are to be stored for 24 hours at ambient temperature ($20 \pm 5^\circ\text{C}$).

电池放置在试验温度等于 $72\pm2^\circ\text{C}$ 的条件下存放至少 6 小时，接着再在试验温度等于 $-40\pm2^\circ\text{C}$ 的条件下存放至少 6 小时。两个极端试验温度之间的最大时间间隔为 30 分钟。此程序重复进行，共完成 10 次，接着将所有试验电池在环境温度($20\pm5^\circ\text{C}$)下存放 24 小时。

Requirement 要求

Batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test battery after testing is not less than 90% of its voltage immediately prior to this procedure.

电池须无渗漏、无泄气、无解体、无破裂和无起火，并且每个试验电池在试验后的开路电压不小于其在进行这一试验前电压的 90%。

T.3. Vibration 振动**Test method 测试方法**

Batteries are firmly secured to the platform of the vibration machine without distorting the cells in such a manner as to faithfully transmit the vibration. The vibration shall be a sinusoidal waveform with a logarithmic sweep between 7 Hz and 200 Hz and back to 7 Hz traversed in 15 minutes. This cycle shall be repeated 12 times for a total of 3 hours for each of three mutually perpendicular mounting positions of the cell. One of the directions of vibration must be perpendicular to the terminal face.

The logarithmic frequency sweep is as follows: from 7 Hz a peak acceleration of 1 gn is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 8 gn occurs (approximately 50 Hz). A peak acceleration of 8 gn is then maintained until the frequency is increased to 200 Hz.

电池紧固于振动台台面，但不得造成电池变形，并能准确可靠地传播振动。振动应是正弦波形，对数扫描频率在 7 Hz 和 200 Hz 之间，再回到 7 Hz，1 次循环时间为 15 分钟。这一振动过程须对三个互相垂直的电池安装方位的每一方向重复进行 12 次，总共为时 3 小时。其中一个振动方向必须与端面垂直。

对数扫频方式：从 7 Hz 开始，保持 1 gn 的最大加速度，直到频率达到 18 Hz。然后将振幅保持在 0.8mm（总位移 1.6mm），并增加频率直到峰值加速度达到 8 gn（频率约为 50 Hz）。将峰值加速度保持在 8 gn 直到频率增加到 200 Hz。

Requirement 要求

Batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test battery after testing is not less than 90% of its voltage immediately prior to this procedure.

电池须无渗漏、无泄气、无解体、无破裂和无起火，并且每个试验电池在试验后的开路电压不小于其在进行这一试验前电压的 90%。

T.4. Shock 冲击**Test method 测试方法**

Batteries are secured to the testing machine by means of a rigid mount which will support all mounting surfaces of each test battery. Each battery is subjected to a half-sine shock of peak acceleration of 150 gn and pulse duration of 6 milliseconds. Each battery is subjected to three shocks in the positive direction followed by three shocks in the negative direction of three mutually perpendicular mounting positions of the battery for a total of 18 shocks.

试验电池用刚性支架紧固在试验装置上，支架支撑着每个试验电池组的所有安装面。每个电池须经受峰值加速度 150 gn 和脉冲持续时间 6 ms 的半正弦波冲击。每个电池须在三个互相垂直的电池安装方位的正方向经受三次冲击，接着在反方向经受三次冲击，总共经受 18 次冲击。

Requirement 要求

Batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test battery after testing is not less than 90% of its voltage immediately prior to this procedure.

电池须无渗漏、无泄气、无解体、无破裂和无起火，并且每个试验电池在试验后的开路电压不小于其在进行这一试验前电压的 90%。

T.5. External short circuit 外部短路**Test method 测试方法**

Batteries to be tested are temperature stabilized so that its external case temperature reaches $55 \pm 2^{\circ}\text{C}$ and then the battery are subjected to a short circuit condition with a total external resistance of less than 0.1 ohm at $55 \pm 2^{\circ}\text{C}$. This short circuit condition is continued for at least one hour after the battery external case temperature has returned to $55 \pm 2^{\circ}\text{C}$. The battery is observed for a further six hours for the test to be concluded.

试验电池在测试温度下放置至稳定状态，使其外壳温度达到 $55 \pm 2^{\circ}\text{C}$ ，然后使电池在 $55 \pm 2^{\circ}\text{C}$ 下经受总外电阻小于 0.1Ω 的短路条件。短路测试持续到电池外壳温度回到 $55 \pm 2^{\circ}\text{C}$ 后继续至少 1 小时。试验电池被观察 6 小时再下结论。

Requirement 要求

Batteries meet this requirement if their external temperature does not exceed 170°C and there is no disassembly, no rupture and no fire within six hours after test.

电池外壳温度不超过 170°C ，并且在试验过程中及试验后 6 小时内无解体、无破裂，无起火。

T.6. Impact / Crush 撞击/挤压

Test method – Impact (applicable to cylindrical cells not less than 18.0 mm in diameter)

测试方法 – 撞击 (适用于直径大于等于 18.0 毫米以上的圆柱形电池)

The sample cell or component cell is to be placed on a flat smooth surface. A 15.8 mm $\pm$ 0.1mm diameter, at least 6 cm long, or the longest dimension of the cell, whichever is greater, Type 316 stainless steel bar is to be placed across the centre of the sample. A 9.1 kg $\pm$ 0.1 kg mass is to be dropped from a height of 61 $\pm$ 2.5 cm at the intersection of the bar and sample in a controlled manner using a near frictionless, vertical sliding track or channel with minimal drag on the falling mass. The vertical track or channel used to guide the falling mass shall be oriented 90 degrees from the horizontal supporting surface.

The test sample is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the 15.8 mm $\pm$ 0.1mm diameter curved surface lying across the centre of the test sample. Each sample is to be subjected to only a single impact.

试样电池或电池组放在平坦光滑表面上。一根 316 型不锈钢棒横放在试样中心，钢棒直径 15.8 毫米 $\pm$ 0.1 毫米，长度至少 6 厘米，或电池最长端的尺度，取二者之长者。将一块 9.1 千克 $\pm$ 0.1 千克的重锤从 61 $\pm$ 2.5 厘米高度跌落到钢棒和试样交叉处，使用一个几乎没有摩擦的、对落体重锤阻力最小的垂直轨道或管道加以控制。垂直轨道或管道用于引导落锤沿与水平支撑表面呈 90 度落下。

受撞击的试样，纵轴应于平坦表面平行并与横放在试样中心的直径 15.8 $\pm$ 0.1 毫米弯曲表面的纵轴垂直。每一试样只经受一次撞击。

Test method – Crush (applicable to prismatic, pouch, coin/button cells and cylindrical cells less than 18.0 mm in diameter)

测试方法 – 挤压 (适用于棱形，袋，硬币/纽扣电池和圆柱形电池直径小于 18.0 毫米)

A component cell is to be crushed between two flat surfaces. The crushing is to be gradual with a speed of approximately 1.5 cm/s at the first point of contact. The crushing is to be continued until the first of the three options below is reached.

- (a) The applied force reaches 13 kN $\pm$ 0.78 kN;
- (b) The voltage of the cell drops by at least 100 mV; or
- (c) The cell is deformed by 50% or more of its original thickness.

Once the maximum pressure has been obtained, the voltage drops by 100 mV or more, or the cell is deformed by at least 50% of its original thickness, the pressure shall be released.

A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis.

Each component cell is to be subjected to one crush only. The test sample shall be observed for a further 6 h. The test shall be conducted using component cells that have not previously been subjected to other tests.

将电芯放在两个平面之间挤压，挤压力度逐渐加大，在第一个接触点上的速度大约为 1.5 cm/s。挤压持续进行，直到出现以下三种情况之一：

- (a)施加的力量达到 13 kN $\pm$ 0.78 kN;
- (b)电芯的电压下降至少 100mV；或
- (c)电芯形变达原始厚度的 50%或更多。

一旦达到最大压力、电压下降 100mV 或更多，或电芯形变至少达原厚度的 50%，即可解除压力。

棱柱形或袋装电池须从最宽的面施压。纽扣/硬币形电池应从其平坦表面施压。圆柱形电池应从与纵轴垂直的方向施压。

每个试样电芯只做一次挤压试验。试样须继续观察 6 小时。试验须使用之前未做过其他试验的电芯进行。

Requirement 要求

Component cells meet this requirement if their external temperature does not exceed 170°C and there is no disassembly and no fire within six hours after the test.

电芯外壳温度不超过 170°C，并且在试验过程中及试验后 6 小时内无解体，无起火。

T.7. Overcharge 过充电**Test method 测试方法**

The charge current is twice the manufacturer's recommended maximum continuous charge current. The minimum voltage of the test shall be as follows:

- (a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test is the lesser of two times the maximum charge voltage of the battery or 22V.
- (b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage.

Tests are to be conducted at ambient temperature. The duration of the test shall be 24 hours.

充电电流为制造商建议的最大持续充电电流的两倍。试验的最小电压如下：

- (a) 制造商建议的充电电压不大于 18 伏时，试验的最小电压应是电池组最大充电电压的两倍或 22 伏两者中的较小者。
- (b) 制造商建议的充电电压大于 18 伏时，试验的最小电压应是电池组最大充电电压的 1.2 倍。

试验应在环境温度下进行。进行试验的时间应为 24 小时。

Requirement 要求

Batteries meet this requirement if there is no disassembly and no fire during the test and within seven days after the test.

电池在试验过程中和试验后 7 天内无解体，无起火。

T.8. Forced discharge 强制放电**Test method 测试方法**

Each component cell is forced discharged at ambient temperature by connecting it in series with a 12V D.C. power supply at an initial current equal to the maximum discharge current specified by the manufacturer.

The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell. Each cell is forced discharged for a time interval (in hours) equal to its rated capacity divided by the initial test current (in ampere).

每个电芯在环境温度下与 12V 直流电电源串联在起始电流等于制造商给定的最大放电电流的条件下强制放电。


电芯与一个适当大小的电阻负载串联以调节到规定大小的放电电流。每块电芯的放电时间（单位为 h）等于电芯的额定容量除以试验初始放电电流（单位 A）。

Requirement 要求

Component cells meet this requirement if there is no disassembly and no fire during the test and within seven days after the test.

电芯在试验过程中和试验后 7 天内无解体，无起火。

V、Test Procedure 测试流程



VI、Main Test Apparatus 主要测试仪器

Serial No. 设备编号	Name of Equipment 设备名称	Model 型号	Calibration Date /Due Date 校准日期/到期日
NCT-030	Rechargeable battery test system 充电电池测试系统	R2D6-5V-5A	2015. 08. 26
			2016. 08. 25
NCT-012	Vacuum chamber (for battery test) 电池测试真空箱	GX-3020-Z	2016. 03. 07
			2017. 03. 06
NCT-017	Temperature circulation chamber 温度循环设备	GX-3000-150LT	2016. 03. 07
			2017. 03. 06
NCT-021	Vibration test instrument 振动测试仪器	ES-3-150	2016. 03. 07
			2017. 03. 06
NCT-022	Shock test instrument 冲击测试仪器	SY10-2	2016. 03. 07
			2017. 03. 06
NCT-018	Battery short circuit test instrument 电池短路测试仪器	BE-1000W	2016. 03. 07
			2017. 03. 06
NCT-019	Impact test instrument 撞击测试仪器	BE-5066	2016. 03. 07
			2017. 03. 06
NCT-020	Crush test instrument 挤压测试仪器	BE-6045T	2016. 03. 07
			2017. 03. 06
NCT-033	DC regulated power supply 直流稳压电源	PS1540	2015. 08. 26
			2016. 08. 25
NCT-024	Battery anti-explosion chamber 电池防爆箱	GX-FB-200	2016. 03. 07
			2017. 03. 06
NCT-003	Electronic Balance 电子天平	JC-223S	2016. 03. 07
			2017. 03. 06
NCT-008	Electronic Balance 电子天平	JSC-S30	2016. 03. 07
			2017. 03. 06
NCT-001	Digital Multimeter 数字万用表	17B+	2016. 03. 07
			2017. 03. 06
NCT-029	Data acquisition unit 数据采集器	34970A	2016. 03. 07
			2017. 03. 06

VII、Test Data 测试数据

T.1. Altitude simulation 高度模拟

The state of cells 样品状态	No. 编号	Pre-test 试验前		After test 试验后		Mass loss 质量损失 (%)	Voltage after test/Voltage pre-test 试验后电压/试验前电压(%)	Status 结果
		Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltage 电压 (V)			
Full charged after one cycle 一次循环后 满电状态	B1#	9.107	4.19	9.103	4.18	0.044	99.76	Pass 合格
	B2#	9.033	4.18	9.030	4.18	0.033	100.00	Pass 合格
	B3#	9.026	4.18	9.023	4.18	0.033	100.00	Pass 合格
	B4#	8.948	4.19	8.944	4.18	0.045	99.76	Pass 合格
	B5#	8.772	4.19	8.768	4.19	0.046	100.00	Pass 合格
	B6#	8.653	4.18	8.650	4.18	0.035	100.00	Pass 合格
	B7#	8.768	4.19	8.764	4.18	0.046	99.76	Pass 合格
	B8#	9.347	4.19	9.344	4.18	0.032	99.76	Pass 合格
	B9#	8.992	4.19	8.988	4.19	0.044	100.00	Pass 合格
	B10#	9.105	4.18	9.102	4.18	0.033	100.00	Pass 合格

Notes 注释: Atmospheric pressure 大气压强: $1.013 \times 10^5 \text{Pa}$, Ambient temperature 环境温度: 22.0°C
 After the test, there is no leakage, no venting, no disassembly, no rupture and no fire.
 测试后, 电池未渗漏、未泄气、未解体、未破裂和未起火。

T.2. Thermal test 温度试验

The state of cells 样品状态	No. 编号	Pre-test 试验前		After test 试验后		Mass loss 质量损失 (%)	Voltage after test/Voltage pre-test 试验后电压/试验前电压(%)	Status 结果
		Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltage 电压 (V)			
Full charged after one cycle 一次循环后 满电状态	B1#	9.103	4.18	9.091	4.17	0.132	99.76	Pass 合格
	B2#	9.030	4.18	9.018	4.17	0.133	99.76	Pass 合格
	B3#	9.023	4.18	9.011	4.17	0.133	99.76	Pass 合格
	B4#	8.944	4.18	8.934	4.17	0.112	99.76	Pass 合格
	B5#	8.768	4.19	8.758	4.18	0.114	99.76	Pass 合格
	B6#	8.650	4.18	8.639	4.17	0.127	99.76	Pass 合格
	B7#	8.764	4.18	8.754	4.17	0.114	99.76	Pass 合格
	B8#	9.344	4.18	9.334	4.17	0.107	99.76	Pass 合格
	B9#	8.988	4.19	8.977	4.18	0.122	99.76	Pass 合格
	B10#	9.102	4.18	9.089	4.17	0.143	99.76	Pass 合格

Notes 注释: Atmospheric pressure 大气压强: $1.013 \times 10^5 \text{Pa}$, Ambient temperature 环境温度: 22.0°C
 After the test, there is no leakage, no venting, no disassembly, no rupture and no fire.
 测试后, 电池未渗漏、未泄气、未解体、未破裂和未起火。

T.3. Vibration 振动

The state of cells 样品状态	No. 编号	Pre-test 试验前		After test 试验后		Mass loss 质量损失 (%)	Voltage after test/Voltage pre-test 试验后电压/试验前电压 (%)	Status 结果
		Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltage 电压 (V)			
Full charged after one cycle 一次循环后 满电状态	B1#	9.091	4.17	9.087	4.16	0.044	99.76	Pass 合格
	B2#	9.018	4.17	9.015	4.16	0.033	99.76	Pass 合格
	B3#	9.011	4.17	9.007	4.17	0.044	100.00	Pass 合格
	B4#	8.934	4.17	8.930	4.17	0.045	100.00	Pass 合格
	B5#	8.758	4.18	8.755	4.17	0.034	99.76	Pass 合格
	B6#	8.639	4.17	8.635	4.17	0.046	100.00	Pass 合格
	B7#	8.754	4.17	8.750	4.16	0.046	99.76	Pass 合格
	B8#	9.334	4.17	9.331	4.17	0.032	100.00	Pass 合格
	B9#	8.977	4.18	8.974	4.17	0.033	99.76	Pass 合格
	B10#	9.089	4.17	9.085	4.17	0.044	100.00	Pass 合格

Notes 注释: Atmospheric pressure 大气压强: 1.013×10^5 Pa, Ambient temperature 环境温度: 21.5°C
After the test, there is no leakage, no venting, no disassembly, no rupture and no fire.
测试后, 电池未渗漏、未泄气、未解体、未破裂和未起火。

T.4. Shock 冲击

The state of cells 样品状态	No. 编号	Pre-test 试验前		After test 试验后		Mass loss 质量损失 (%)	Voltage after test/Voltage pre-test 试验后电压/试验前电压 (%)	Status 结果
		Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltage 电压 (V)			
Full charged after one cycle 一次循环后 满电状态	B1#	9.087	4.16	9.085	4.16	0.022	100.00	Pass 合格
	B2#	9.015	4.16	9.011	4.16	0.044	100.00	Pass 合格
	B3#	9.007	4.17	9.003	4.16	0.044	99.76	Pass 合格
	B4#	8.930	4.17	8.926	4.16	0.045	99.76	Pass 合格
	B5#	8.755	4.17	8.751	4.17	0.046	100.00	Pass 合格
	B6#	8.635	4.17	8.630	4.16	0.058	99.76	Pass 合格
	B7#	8.750	4.16	8.746	4.16	0.046	100.00	Pass 合格
	B8#	9.331	4.17	9.328	4.16	0.032	99.76	Pass 合格
	B9#	8.974	4.17	8.971	4.17	0.033	100.00	Pass 合格
	B10#	9.085	4.17	9.081	4.16	0.044	99.76	Pass 合格

Notes 注释: Atmospheric pressure 大气压强: 1.013×10^5 Pa, Ambient temperature 环境温度: 21.5°C
After the test, there is no leakage, no venting, no disassembly, no rupture and no fire.
测试后, 电池未渗漏、未泄气、未解体、未破裂和未起火。

T.5. External short circuit 外部短路

The state of cells 样品状态	No. 编号	External Peak temperature(°C) 电池表面最高温度(°C)	Status 结果
Full charged after one cycle 一次循环后满电状态	B1#	55.9	Pass 合格
	B2#	56.2	Pass 合格
	B3#	55.7	Pass 合格
	B4#	55.7	Pass 合格
	B5#	55.8	Pass 合格
	B6#	55.7	Pass 合格
	B7#	56.0	Pass 合格
	B8#	55.6	Pass 合格
	B9#	55.8	Pass 合格
	B10#	55.8	Pass 合格
Notes 注释: Atmospheric pressure 大气压强: $1.013 \times 10^5 \text{ Pa}$, Ambient temperature 环境温度: 21.5°C There is no disassembly, no rupture and no fire within six hours after test. 电池在测试后 6 小时内未解体、未破裂, 未起火。			

T.6. Crush 挤压

The state of cells 样品状态	No. 编号	External Peak temperature(°C) 电池表面最高温度(°C)	Status 结果
50% charged after one cycle 一次循环后 50% 充电状态	C19#	26.1	Pass 合格
	C20#	25.7	Pass 合格
	C21#	25.6	Pass 合格
	C22#	25.8	Pass 合格
	C23#	25.7	Pass 合格
Notes 注释: Atmospheric pressure 大气压强: $1.013 \times 10^5 \text{ Pa}$, Ambient temperature 环境温度: 21.5°C There is no disassembly, no rupture and no fire within six hours after test. 电芯在测试后 6 小时内未解体、未破裂, 未起火。			

T.7. Overcharge 过充电

The state of cells 样品状态	No. 编号	Status 结果
Full charged after one cycle 一次循环后满电状态	B11#	Pass 合格
	B12#	Pass 合格
	B13#	Pass 合格
	B14#	Pass 合格

Full charged after fifty cycles 五十次循环后满电状态	B15#	Pass 合格
	B16#	Pass 合格
	B17#	Pass 合格
	B18#	Pass 合格
Notes 注释: Atmospheric pressure 大气压强: 1.013×10^5 Pa, Ambient temperature 环境温度: 21.5℃ There is no disassembly and no fire during the test and within seven days after the test. 电池在测试中和测试后 7 天内未解体, 未起火。		

T.8. Forced discharge 强制放电

The state of cells 样品状态	No. 编号	Status 结果
Full discharged after one cycle 一次循环完全放电状态	C24#	Pass 合格
	C25#	Pass 合格
	C26#	Pass 合格
	C27#	Pass 合格
	C28#	Pass 合格
	C29#	Pass 合格
	C30#	Pass 合格
	C31#	Pass 合格
	C32#	Pass 合格
	C33#	Pass 合格
Full discharged after fifty cycles 50 个循环完全放电状态	C34#	Pass 合格
	C35#	Pass 合格
	C36#	Pass 合格
	C37#	Pass 合格
	C38#	Pass 合格
	C39#	Pass 合格
	C40#	Pass 合格
	C41#	Pass 合格
	C42#	Pass 合格
	C43#	Pass 合格
Notes 注释: Atmospheric pressure 大气压强: 1.013×10^5 Pa, Ambient temperature 环境温度: 22.0℃ There is no disassembly and no fire during the test and within seven days after the test. 电芯在测试中和测试后 7 天内未解体, 未起火。		

VIII、Conclusion 结论

No. 编号	Test item 测试项目	Sample number 样品数量	Test reference 测试参考	Conclusion 结论
1	Altitude simulation 高空模拟	B1#~B10#	UN Manual of Test and Criteria, part III, subsection 38.3.4.1 UN 试验和标准手册,第III部分,第 38.3.4.1 节	Pass 合格
2	Thermal test 温度试验		UN Manual of Test and Criteria, part III, subsection 38.3.4.2 UN 试验和标准手册,第III部分,第 38.3.4.2 节	Pass 合格
3	Vibration 振动		UN Manual of Test and Criteria, part III, subsection 38.3.4.3 UN 试验和标准手册,第III部分,第 38.3.4.3 节	Pass 合格
4	Shock 冲击		UN Manual of Test and Criteria, part III, subsection 38.3.4.4 UN 试验和标准手册,第III部分,第 38.3.4.4 节	Pass 合格
5	External short circuit 外部短路	C19#~C23#	UN Manual of Test and Criteria, part III, subsection 38.3.4.5 UN 试验和标准手册,第III部分,第 38.3.4.5 节	Pass 合格
6	Impact/Crush 撞击/挤压		UN Manual of Test and Criteria, part III, subsection 38.3.4.6 UN 试验和标准手册,第III部分,第 38.3.4.6 节	Pass 合格
7	Overcharge 过度充电	B11#~B18#	UN Manual of Test and Criteria, part III, subsection 38.3.4.7 UN 试验和标准手册,第III部分,第 38.3.4.7 节	Pass 合格
8	Forced discharge 强制放电	C24#~C43#	UN Manual of Test and Criteria, part III, subsection 38.3.4.8 UN 试验和标准手册,第III部分,第 38.3.4.8 节	Pass 合格

The submitted samples were complied with the stated requirements of UN manual of test and criteria, part III, subsection 38.3

经检测，提交的测试样品均符合 UN38.3 的要求，测试结论为合格。

IX、Photo of The Sample 样品图片

Model 型号: LP432543




Photo 1 Front 正面




Photo 2 Rear 反面




Photo 3 Internal Cell 内部电芯




Photo 4 Internal Cell 内部电芯




Photo 5 Protection board 保护板




Photo 6 Protection board 保护板

注意事项**Important Notice**

1. The test report is invalid without the official stamp of NCT.

本报告书无 NCT 盖章无效。

2. Nobody is allowed to photocopy or partly photocopy this test report without written permission of NCT.

未经 NCT 书面同意，不得复制或部分地复制本报告书。

3. The test report is invalid without the signatures of Ratifier, Reviewer and Testing engineer.

本报告书无批准人、审核人、及主检人签名无效。

4. The report is invalid when anything of following happens – illegal transfer, reproduce, embezzlement, imposture, modification or tampering in any media form.

私自转让、复制、盗用、冒用、涂改、或以任何媒体形式篡改的报告书无效。

5. Objections to the test report must be submitted to NCT within 15 days.

对报告书若有异议，应于收到报告之日起 15 天内向本公司提出。

6. The test report is valid for the tested samples only.

本报告仅对测试样品有效。

7. The Chinese contents in this report are only for reference.

本报告中的中文内容仅供参考。

*******End of Report 报告结束*******